

## Gold Plating

*Dynatronix makes no warranty as to the accuracy of the information contained herein. Information has been compiled from numerous sources and may be subject to inaccuracies. Dynatronix reserves the right to make changes and/or corrections to the data herein. Information presented consists of generally-accepted operating parameters used in the metal finishing industry. This information is provided for convenience only, and is not to be construed as specific recommendations by Dynatronix, Inc. Power supply recommendations are for initial settings when first setting up the process. Actual operational settings may vary depending on the substrate, chemistry, operating parameters, and actual testing by the end-user.*

Common Name	Also Known as	Typical Bath Constituents	Power Supply Recommendations	Typical Pulse Settings (if Used)	Typical Operating Parameters
<b>Antique Gold (Orange-Brown)</b>	Classes A, B	Gold as $\text{KAu}(\text{CN})_2$ (6 g/L)	<1% ripple	High Frequency (HFP); Do Not Use Low Frequency Pulse (LFP)	Anodes: 316 SS
		Sodium Hydroxide (15 g/L)	Amp-hr meter (gold metal additions based on A-hr meter readings)	Duty Cycle: 50%	Filter Periodically
		Sodium Carbonate (30 g/L)	Straight DC (Pulse Optional, but not Typical)	1 ms ON Time	Agitation: Not Required
		Sodium Cyanide (4 g/L)	Totalizer (tracks gold usage to prevent misuse or theft)	1 ms OFF Time	Operating temp: 160 to 180 F
					Typical pH (range): 10 to 11
					Output Voltage (Power Supply Max Rating): 6 VDC
					Current Density: 30-40 ASF (3.0-4.0 ASD)